

A-C® Additives for PVC Pipe Extrusion

In pipe extrusion, A-C® polyethylene waxes can provide increased output rates, reduced plate-out and an increased filler level, maintaining physical properties and enhanced surface quality.



PROPERTIES:

| Product | A-C 6A | A-C 16A | A-C 617A | A-C 629A | A-C 680A | A-C 316A | A-C 400A |
|------------------------------|--------------------------|---------|----------|-----------------------------------|----------|------------------------------------|----------------------------------|
| Type of polyethylene wax | Low density homopolymers | | | Oxidized low density homopolymers | | Oxidized high density homopolymers | Ethylene vinyl acetate copolymer |
| Drop point (°C) | 106 | 102 | 102 | 104 | 108 | 140 | 92 |
| Viscosity (cps 140°) | 375 | 525 | 180 | 200 | 250 | 8500 (150 °C) | 595 |
| Acid number (mg KOH/g) | 0 | 0 | 0 | 16 | 16 | 16 | 13% vinyl acetate |
| Density (g/cm ³) | 0.92 | 0.91 | 0.91 | 0.93 | 0.93 | 0.98 | 0.92 |
| Dosage (phr) | 0.1 - 0.4 | | | 0.1 - 0.4 | | 0.05 - 0.2 | 0.1 - 0.4 |

BENEFITS:

| Product | Performance in PVC pipe extrusion |
|-------------------------------|--|
| A-C 6A A-C 16A A-C 617A | Excellent external lubrication leading to high output rates and enhanced gloss and surface quality; delay fusion |
| A-C 629A A-C 680A | Optimal combination of external lubrication, metal release, and gloss. Slightly improve fusion |
| A-C 316A | Superior additives for metal release. Very effective fusion acceleration enables controlled pressure build-up in the extruder; excellent distribution of filler in the melt; increased melt homogeneity; reduced gloss |
| A-C 400A | Reduce melt pressure, improve filler dispersion |

For additional information or to contact us, please visit:
honeywell-additives.com



A-C is a registered trademark of Honeywell International Inc.

PA | April 2017
©2017 Honeywell International Inc.
All rights reserved

All statements and information provided herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, express or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated herein, or that other measures may not be required. User assumes all liability for use of the information and results obtained.