

**Honeywell A-C® Performance Additives for Paints Coatings and Inks**

## Typical Properties

	Mettler Drop Point (ASTM D-3954)	Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
<b>Polyethylene Homopolymers</b>						
A-C 820A <sup>(1)</sup>	126°C 259°F	1.0	0.97	80	Nil	Powder
A-C 1810A <sup>(1)</sup>	121°C 250°F	2.0	0.95	20	Nil	Powder
A-C 9, 9A, 9F	115°C 239°F	0.5	0.93	450	Nil	Prill, Powder, Fine Powder
A-C 8, 8A	113°C 235°F	1.0	0.93	450	Nil	Prill, Powder
A-C 3A	112°C 234°F	2.0	0.92	450	Nil	Powder
A-C 7, 7A	109°C 228°F	2.5	0.92	450	Nil	Prill, Powder
A-C 6, 6A	106°C 223°F	4.0	0.92	375	Nil	Prill, Powder
A-C 16 <sup>(8)</sup> , 16A	102°C 216°F	5.5	0.91	525	Nil	Prill, Powder
A-C 617, 617A	101°C 214°F	7.0	0.91	180	Nil	Prill, Powder
A-C 1702 <sup>(2)</sup>	90°C 194°F	98 <sup>(3)</sup>	0.88	30	Nil	Grease-like
<b>Oxidized Polyethylene Homopolymers</b>						
A-C 673P	110°C 230°F	<1.0	0.95	400	17	Pastille
A-C 680	108°C 226°F	1.5	0.93	250	16	Prill
A-C 655	107°C 225°F	2.5	0.93	210	16	Prill
A-C 629, 629A	101°C 214°F	5.5	0.93	200	15	Prill, Powder
A-C 656	98°C 208°F	9.0	0.92	185	15	Prill
A-C 6702 <sup>(5)</sup>	88°C 190°F	90 <sup>(3)</sup>	0.85	35	15	Grease-like
<b>High-Density Oxidized Polyethylene Homopolymers</b>						
A-C 307, 307A	140°C 284°F	<0.5	0.98	85,000 @150°C	7	Granule, Powder
A-C 316, 316A	140°C 284°F	<0.5	0.98	8,500 @150°C	16	Granule, Powder
A-C 325	136°C 277°F	<0.5	0.99	4,500 @150°C	25	Granule
A-C 392	138°C 280°F	<0.5	0.99	4,500 @150°C	30	Granule
A-C 330	137°C 279°F	<0.5	0.99	3,600 @150°C	30	Granule
A-C 395, 395A	137°C 279°F	<0.5	1.00	2,500 @150°C	41	Granule, Powder
<b>Polypropylene Homopolymers</b>						
	Softening Point					
A-C 1754	167°C 333°F	<0.5	0.89	775 @190°C	Nil	Powder
A-C 1660	150°C 302°F	<0.5	0.89	60 @190°C	Nil	Powder
A-C 1089	146°C 295°F	<0.5	0.91	45 @190°C	Nil	Powder
<b>Ethylene-Acrylic Acid Copolymers</b>						
A-C 540, 540A	105°C 221°F	2.0	0.93	575	40	Prill, Powder
A-C 580	95°C 203°F	4.0	0.93	650	75	Prill
A-C 5120 <sup>(6)</sup>	92°C 198°F	8.0	0.93	600	120	Prill

# Honeywell A-C® Performance Additives for Paints Coatings and Inks

## Typical Properties

	Mettler Drop Point (ASTM D-3954)	Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
--	-------------------------------------	-----------------------------	--------------------------------	---------------------------------------	--	---------------

### Ethylene-Vinyl Acetate Copolymers

A-C 405T	102°C 216°F	4.0	0.92	600	6% Vinyl Acetate	Prill
A-C 405M	100°C 212°F	5.0	0.92	600	8.5% Vinyl Acetate	Prill
A-C 405S	94°C 201°F	7.0	0.92	600	10.5% Vinyl Acetate	Prill
A-C 400, 400A	92°C 198°F	9.5	0.92	595	13% Vinyl Acetate	Prill, Powder
A-C 415	89°C 192°F	12.5	0.92	1,300	15% Vinyl Acetate	Prill
A-C 430 <sup>(8)</sup>	75°C 167°F	70 <sup>(7)</sup>	0.93	600	26% Vinyl Acetate	Tacky solid

### Oxidized Ethylene-Vinyl Acetate Copolymers

A-C 645 P	99°C 210°F	5.0	0.94	375	13 (SAP=56)	Pastille
-----------	------------	-----	------	-----	-------------	----------

	Melt. Point (DSC)	Cation Type	Viscosity cps, @190°C (Brookfield)	Acid Number, mg KOH/g (ASTM D-1386)	Physical Form
--	-------------------	-------------	---------------------------------------	--	---------------

### AClyn® Low Molecular Weight Ionomers

AClyn 201 <sup>(8)</sup> , 201A <sup>(8)</sup>	102°C 215°F	Ca	5,500	42	Granular, Powder
AClyn 295, 295A <sup>(8)</sup>	99°C 210°F	Zn	4,500	Nil	Granular, Powder
AClyn 246 <sup>(8)</sup> , 246A <sup>(8)</sup>	95°C 203°F	Mg	7,000	Nil	Granular, Powder
AClyn 285 <sup>(8)</sup> , 285A <sup>(8)</sup>	82°C 180°F	Na	80,000	20	Granular, Powder

	Mettler Drop Point (ASTM D-3954)	Hardness, dmm (ASTM D-5)	Density, g/cc (ASTM D-1505)	Viscosity cps, @140°C (Brookfield)	Saponification# mg KOH/g	% MAH Bound	Bound SAP# mg KOH/g	Physical Form
--	-------------------------------------	-----------------------------	--------------------------------	---------------------------------------	-----------------------------	----------------	------------------------	---------------

### Ethylene Maleic Anhydride Copolymers

A-C 573A, 573P	106°C 223°F	4.5	0.92	600	5	95+%	5	Powder, Pastille
A-C 575A, 575P	106°C 223°F	4.5	0.92	4,200	35	95+%	33	Powder, Pastille

### Propylene Maleic Anhydride Copolymers

	Softening Point							
A-C 597P	141°C 286°F	<0.5	0.94	350 @190°C	87	72%	63	Powder, Pastille
A-C 907P	152°C 306°F	<0.5	0.93	350 @190°C	87	70%	60	Pastille
A-C 596A, 596P	141°C 286°F	<0.5	0.93	150 @190°C	50	85%	43	Powder, Pastille
A-C 950P	149°C 300°F	<0.5	0.93	2,000 @190°C	50	65%	33	Pastille
A-C 1325P	149°C 300°F	<0.5	0.93	1,600 @190°C	18	78%	14	Pastille

#### Notes:

- (1) Product only available as a powder
- (2) Product only available in fiber drums or slabs
- (3) Product has a grease-like consistency, hardness ASTM D-1321
- (4) Product only available in steel drums
- (5) Product only available in fiber or steel drums
- (6) Product only available in fiber drums
- (7) Product is a tacky solid, hardness ASTM D-1321
- (8) Minimum order quantities and extended order lead times may apply.

**For additional information or to contact us, please visit:**  
[honeywell-additives.com](http://honeywell-additives.com)

All statements, information and data given herein are believed to be accurate and reliable, but are presented without guarantee, warranty or responsibility of any kind, expressed or implied. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not recommendations to infringe any patent. The user should not assume that all safety measures are indicated, or that measures may not be required.



RESPONSIBLE CARE®  
OUR COMMITMENT TO SUSTAINABILITY

1777 PA | v1 | October 2017

©2017 Honeywell International Inc. All rights reserved.

**Honeywell**