

A-C[®] 1702

Grease like, low temperature, completely amorphous, low density polyethylene (PE) homopolymer for use in solvent borne coatings; heat set, sheet fed solvent borne inks; and specialty digital and UV/EB inks to provide mar and rub resistance by lowering the coefficient of friction. Also used in lubricants to provide release. Will act as a plasticizer in paraffin based candles, especially large volume candles, to resist cracking.

TYPICAL PROPERTIES

Property	Value
Hardness	98
Viscosity @ 140° C	30
Drop Point, Mettler	90°C (194°F)
Density	0.88
Acid Number	Nil

REGULATORY APPROVALS

Property	Value
Plastic Pipe Institute/NSF*	No
FDA Indirect Approvals*	No

PRODUCT FORM AND SIZE

Property	Value
Product Form	Grease like

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

@ 2021 Honeywell International Inc.

All rights reserved

