

Honeywell Titan™ 7686

Polymers for Asphalt Modification

7686

Honeywell Titan™ 7686 can be used to modify asphalt for paving applications.

TYPICAL PROPERTIES:

| Property | Value |
|--------------------------------------|---------------|
| Hardness @ 25°C (77°F) | <0.5 dmm |
| Drop Point, Mettler | 137°C (279°F) |
| Density | 0.99 g/cc |
| Viscosity @ 150°C (302°F) Brookfield | 4,500 cps |
| Acid Number | 25 mg KOH/g |

PRODUCT FORM AND PACKAGING:

| Property | Value |
|--------------|--|
| Product Form | granule |
| Size | 100% minus 5 mesh |
| Bulk Density | 625 kg/m ³ (37 lb/ft ³) |
| Packaging | 1,000 kg Super Sacks Other packaging options may be available |

SAFETY PRECAUTIONS:

Honeywell polymers are regarded as non-hazardous when exposure is controlled by using accepted industrial hygiene practices. Consult our Material Safety Data Sheet for specific recommendations on safe handling.

OFFICES: Honeywell
Corporate Headquarters
101 Columbia Road
Morristown NJ, 07962
Tech Assistance: 973-455-5382
Customer Service: 973-455-2145
Toll Free in US:
Tech Assistance: 800-451-9961
Customer Service: 888-245-4738

**Europe / Middle East /
Africa / India**
Honeywell Belgium NV
Interleuvenlaan 15i
3001 Heverlee, Belgium
Telephone: +32 16 39 12 11
Fax: +32 16 40 00 33

Asia / Pacific
Honeywell
No.430, Li Bing Road, Zhangjiang
Hi-Tech Zone, Shanghai 201203
China
Telephone: +8621 2894-2000
Fax: +8621 5855-3543

WEBSITE: www.honeywell-titan.com

DISCLAIMER: Although all statements and information contained herein are believed to be accurate and reliable, they are presented without guarantee or warranty of any kind, express or implied. Information provided herein does not relieve the user from the responsibility of carrying out its own tests and experiments, and the user assumes all risks and liability for use of the information and results obtained. Statements or suggestions concerning the use of materials and processes are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe any patent. The user should not assume that all toxicity data and safety measures are indicated herein or that other measures may not be required.

March 2013, Printed in USA
© 2013 Honeywell International Inc.
All rights reserved
AD-SP-124

ISO 9001:2000 Certified

Honeywell